



MASTERANK AMERICA INC

SPECIFICATION

MR 130SW

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>MIN</u>	<u>MAX</u>	<u>TYPICAL</u>
Melting point, °C 59.0	ASTM D 87	54	57.8	56.7
°F		129.2	136	134
Oil Content, wt %	ASTM D 721		0.5	0.3
Color, Saybolt	ASTM D 156	+15		
Viscosity, cSt @ 100°C	ASTM D 445	4.7	7.1	5.2
Density, kg/liter @ 175°F	ASTM D 1298			0.812
Flash Point, °C	ASTM D 92			231
Odor	ASTM D 1833		1	<1
FDA	21CFR 172.886	PASS		PASS

Effective February 1, 2009

2 Corporate Plaza Drive, Suite 125, Newport Beach, CA 92660
Tel 949 719 9668 Fax 949 719 9868 Email masterank@masterank.com