



MASTERANK AMERICA INC

SPECIFICATION

MR 5820

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>MIN</u>	<u>MAX</u>	<u>TYPICAL</u>
Melting point, °C	ASTM D 87	58	60	58.6
°F		136.4	140	137.5
Oil Content, wt %	ASTM D 721		0.5	0.4
Color, Saybolt	ASTM D 156	+28		+30
Penetration, 1/10mm@ 77°F	ASTM D 1321		17	15
Penetration, 1/10mm@ 100°F	ASTM D 1321			46
Viscosity, cSt @ 100°C	ASTM D 445			4.2
Density, kg/liter @ 175°F	ASTM D 1298			0.768
Flash Point, °C	ASTM D 92			231
Odor	ASTM D 1833		1	<1
FDA	21CFR 172.886	PASS		PASS

Effective September 21, 2007

2 Corporate Plaza Drive, Suite 125, Newport Beach, CA 92660
Tel 949 719 9668 Fax 949 719 9868 Email masterank@masterank.com